

Chitosan: A Brief Review on Structure and Tissue Engineering Application

Jamalpoor Zahra

1. Tissue Engineering Department, cellular and molecular research center of Iran University of Medical Sciences, Tehran, Iran

Received: 5 October 2013 / Accepted: 15 February 2014

Abstract:

Tissue engineering is an important therapeutic strategy for present and future medicine. Recently, functional biomaterial researches have been directed towards the development of improved scaffolds for regenerative medicine. Chitosan is a natural polymer from renewable resources, obtained from shell of shellfish, and the wastes of the seafood industry. Many researchers have focused on chitosan as a potential source of bioactive materials in the past few decades. It has novel properties such as biocompatibility, biodegradability, antibacterial, and wound-healing activity. Furthermore, recent studies suggested that chitosan and its derivatives are promising candidates as a supporting material for tissue engineering applications owing to their porous structure, gel forming properties, ease of chemical modification, high affinity to in vivo macromolecules, and so on. In this review, we focus on the skin and bone tissue engineering applications of chitosan.

Key Words: Chitosan, Bone tissue engineering, Scaffold, Natural polymer, Skin tissue engineering.

Introduction

Tissue engineering is a developing science technology and can be applied to improve the numerous clinical situations, including spinal fusion, joint replacement, and fracture nonunion and pathological loss of bones [1]. The tissue engineering applications from synthetic and natural polymer scaffolds have been comprehensively examined for the bone tissue replacement in lab and clinic. The polymer materials are more beneficial than others because of their biocompatibility, mechanical properties, micro-structure and the degradation rate, and these properties can even be precisely controlled by composition and fabrication of scaffold polymer materials. The basic idea in all of these accessions is to seed or grow the cell on the biodegradable polymer scaffold to promote tissues growth and remodeling. During the bone tissue regeneration, cell cannot be directly entrapped, because the environment which is used to create them is brutal for the cells to inhabit [2, 3]. Tissue-engineering systems have attempted to mimic

the function of ECMs by placing cells along with growth factors in synthetic scaffolds that act as temporary ECMs. As the new bone is formed, the temporary scaffold will degrade and be absorbed by the body [4, 5]. In last 15 years bone tissue engineering research has increased dramatically. The design and development of the bone scaffolds depend upon the porosity that provides interconnected pores, suitable mechanical strength, and sufficient micro chemistry of surface. It is friendly to the cell behaviors like proliferation, migration, adhesion, and differentiation [6]. There are many factors for the bone tissue engineering, but all connected one are more of the following key ingredients, (a) harvested cells, (b) recombinant signaling molecules, and (c) three dimensional (3D) matrices [7, 8]. During the tissue regeneration, all of these factors play very important roles in the healing process. In the field of bone tissue engineering three dimensional scaffolds facilitate the cells, the guilds, augment and then regenerate three dimensional tissues. After implanted into the defect sites, the scaffolds are

expected to promote and direct the growth of new bone cells and make the new cells attach to intrinsic tissues nearby by degrading slowly and grow together afterwards. This article focuses on chitosan as natural polymer for skin and bone tissue engineering application.

Chitosan structure and properties

Chitosan, the amino polysaccharide copolymer of 1,4 D-glucosamine and N-acetyl glucosamine (Figure 1) is derived from chitin by alkaline or enzymatic deacetylation[9-12]. Therefore, chitin and chitosan are essentially the same polymer but with arbitrarily defined degrees of deacetylation(DD). Generally, if the DD is more than 40%, the term chitosan is used [13]. Chitosan's biodegradation process is dependent on two main factors; the DD and the distribution of NAG units. This was elucidated in the works of Lee et al. who showed that biodegradation declines sharply when the DD is more than 70% [14], and Aiba et al. who found that chitosans with randomly distributed NAG units are less susceptible to lysozymic degradation than chitosans which have repeated blocks of three consecutive NAG units [15].




Figure 1. Molecular structure of chitosan.

In vitro hydrolysis kinetics of chitosan by lysozymes follows the typical Michaelis-Menten kinetics, where k_m and V_{max} are 15 $\mu\text{g/ml}$ and $0.083 \times 10^{-3} \text{ g/L/min}$, respectively [16]. However, in vivo degradation of chitosan, which in theory parallels the rate of tissue regeneration, is variable. Tomihata et al. reported that only 10% of a chitosan film was degraded after 50 h of exposure to lysozymes and 80% of the dry film weight was retained after 12 week implantation in Wistar rats [16]. In addition to being biodegradable, chitosan is a biocompatible polymer. This stems from chitosan's distinct structural similarities to the mammalian glycosaminoglycans (GAGs), which are a family of heteropolysaccharides in mammals that are located primarily on the surface of cells and in the extracellular matrix (ECM) [17]. These molecules are long unbranched polysaccharides which contain repeating disaccharide units. Each disaccharide unit contains either one of two modified sugars; N-acetyl galactosamine or N-acetyl glucosamine and uronic acid such as glucuronate or iduronate [17].

Chitosan has wide applications in medical fields, such as wound dressing, hypocholesterolemic agents, blood

anticoagulant, antithrombogenic and drug delivery systems, in addition to other fields such as waste-water treatment, food and feed additives, wound-healing materials, cosmetic preparations and textile, paper and film technologies [18, 20].

Tissue engineering applications of chitosan

Skin

Wound healing is a specific biological process related to the general phenomenon of growth and tissue regeneration. Wound healing progresses through a series of interdependent and overlapping stages in which a variety of cellular and matrix components act together to re-establish the integrity of damaged tissue and replacement of lost tissue [21]. The wound-healing process has been described as comprising five overlapping stages, which involve complex biochemical and cellular processes. These are described as hemostasis, inflammation, migration, proliferation and maturation phases. Many studies have been reported on the use of chitosan as a wound-healing accelerator, and in fact there is good evidence that chitosan can beneficially influence every separate stage of wound healing. Chitosan and its derivatives could accelerate wound healing by enhancing the functions of inflammatory cells, such as polymorphonuclear leukocytes (PMN) [22, 24], macrophages and fibroblasts or osteoblasts [25, 30]. It has also been reported that chitosan could increase the tensile strength of wounds [31]. The wound-healing effects of chitosan could be affected by the factors of molecular weight deacetylation degree as well as the state of chitosan[32].

Bone

In bone tissue engineering, the biodegradable substitutes act as a temporary skeleton inserted into the defective sites of skeleton or lost bone sites, in order to support and stimulate bone tissue regeneration while they gradually degrade and are replaced by new bone tissue. Also, for being suitable for use in treating vertebral fracture or related conditions, bone cements must possess: proper injectability, a rapid setting time, appropriate stiffness, bioactivity, low setting temperature, and radio-pacity [33]. Composite materials are now playing predominant role as scaffolds in bone tissue engineering. Chitosan has numerous advantageous properties for orthopedic applications, as described above and elsewhere [34], which make it ideal as a bone graft substituent. Chitosan scaffolds are flexible and their mechanical properties are inferior to those of normal bone, as it is unable to support load bearing bone implants. Moreover, chitosan itself is not osteoconductive, although addition of ceramic materials improves its osteoconductivity and mechanical strength. Chitosan scaffolds alone cannot imitate all the properties of natural bone. The substantial development of composite materials with chitosan mimics all the properties of bone. As proven, calcium phosphate materials are osteoconductive to mimic the inorganic portion of natural bone, while chitosan/HAp composite materials show promise in mimicking the organic portion as well as the

inorganic portion of natural bone. Several studies have been conducted with chitosan/HAP composite materials for bone tissue engineering [34, 45]. Calcium phosphate compounds are of great interest in the field of bone tissue engineering. Hydroxyapatite $[\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2]$ is one of the most stable forms of calcium phosphate and it occurs in the bone as a major component (60 to 65%) [46]. HAP also possesses a variety of uses, including orthopedic, dental and maxillofacial applications. Therefore, HAP has recently emerged as an important compound for artificial bone preparation. It stimulates osteoconduction being gradually replaced by the host bone after implantation. It is being used for orthopedic replacements, especially in bone regeneration and dental implant treatment. The mechanical properties of HAP are poor, though, so it cannot be used for load bearing bone tissues. Polymers have been used to improve the mechanical properties of HAP (compressive strength, Young's modulus, fracture toughness) [47].

Conclusion

Tissue engineering as termed Regenerative Medicine is regarded as an ultimately ideal medical treatment for diseases that have been too difficult to be cured by existing methods. This biomedical engineering is designed to repair injured body parts and restore their functions by using laboratory-grown tissues, materials and artificial implants. For regeneration of failed issues, this biomedical engineering utilizes three fundamental tools: living cell, signal molecules, and scaffold. Chitosan is one of the most promising biomaterials in tissue engineering because it offers a distinct set of advantageous physicochemical and biological properties that qualify them for a variety of tissue regeneration. In this review, we presented the examples of the chitosan applications in bone and skin tissue engineering. However, further improvements in the structure and function of this system, such as optimization of chitosan (molecular weight or DDA), chemical modification using functional groups, and formation of ternary complexes, are still necessary.

References:

1. Lin C-Y, Schek RM, Mistry AS, Shi X, Mikos AG, Krebsbach PH, Hollister SJ. Functional bone engineering using ex vivo gene therapy and topology-optimized, biodegradable polymer composite scaffolds. *Tissue Eng*. 2005; 11(9-10):1589
2. Isenberg BC, Williams C, Tranquillo RT. "Small-diameter artificial arteries engineered in vitro," *Circ Res*. 2006; 98:25
3. Kim BS, Putnam AJ, Kulik TJ, Mooney DJ. Optimizing seeding and culture methods to engineer smooth muscle tissue on biodegradable polymer matrices. *Biotechnol Bioeng*. 1998; 57(1):46
4. Mathieu LM, Mueller TL, Bourban P-E, Pioletti DP, Muller R, Manson J-AE. Architecture and properties of anisotropic polymer composite scaffolds for bone tissue engineering. *Biomaterials*. 2006; 27:905
5. Dimar JR, Glassman SD. The art of bone grafting. *Curr Opin Orthopaed*. 2007; 18(3):226
6. Mikos AG, Bao Y, Cima LG, Ingber DE, Vacanti JP, Langer R. *J Biomed Mater Res*. 1993; 27:183
7. Mathieu LM, Mueller TL, Bourban P-E, Pioletti DP, Muller R, Manson J-AE. *Biomaterials*. 2006; 27:905
8. Shin KC, Kim BS, Kim JH, Park TG, Nam JD, Lee DS. A facile preparation of highly interconnected macroporous PLGA scaffolds by liquid-liquid phase separation II. *Polymer*. 2005; 46:3801
9. Chung, T.W. et al. Growth of human endothelial cells on different concentrations of Gly-Arg-Gly-Asp grafted chitosan surface. *Artificial Organs*. 2003; 27 (2), 155-161
10. Araki, Y. and Ito, E. Pathway of chitosan formation in *Mucor-Rouxii* - enzymatic deacetylation of chitin. *European Journal of Biochemistry*. 1975; 55, 71-78
11. Nordtveit, R.J. et al. Degradation of partially N-acetylated chitosans with hen egg white and human lysozyme. *Carbohydrate Polymers*. 1996; 29 (2), 163-167
12. Lee, K.Y. et al. Blood compatibility and biodegradability of partially N-acetylated chitosan derivatives. *Biomaterials*. 1995; 16 (16), 1211-1216
13. Aiba, S. Studies on chitosan. 4. lysozymic hydrolysis of partially N-acetylated chitosans. *International Journal of Biological Macromolecules*. 1992; 14 (4), 225-228
14. Pangburn, S.H. et al. Lysozyme degradation of partially deacetylated chitin, its films and hydrogels. *Biomaterials*. 1992; 3 (2), 105-108
15. Tomihata, K. and Ikada, Y. In vitro and in vivo degradation of films of chitin and its deacetylated derivatives. *Biomaterials*. 1992; 18 (7), 567-575
16. Griffon, D.J. et al. Chitosan scaffolds: Interconnective pore size and cartilage engineering. *Acta Biomaterialia*. 2006; 2 (3), 313-320.
17. Freyman TM, Yannas IV, Gibson LJ. Cellular materials as porous scaffolds for tissue engineering. *Prog Mater Sci*. 2001; 46:273-82.
18. Seyrek, E. and Dubin, P. Glycosaminoglycans as polyelectrolytes. *Advances in Colloid and Interface Science*. 2010; 158 (1-2), 119-129
19. Hirano, S. Chitin biotechnology applications. *Biotechnology Annual Review*. 1996; 2, 237-258.
20. Struszczyk, M.H. Chitin and chitosan - Part II. Applications of chitosan. *Polimery*. 2002; 47 (6), 396-403.
21. Ueno H, Mori T, Fujinaga T. Topical formulations and wound healing applications of chitosan. *Adv Drug Deliv Rev*. 2001; 52(2):105-115.
22. Boateng JS, Matthews KH, Stevens HN, et al. Wound healing dressings and drug delivery systems: a review. *J Pharm Sci*. 2008; 97(8):2892-2923.
23. Santos TC, Marques AP, Silva SS, et al. In vitro evaluation of the behaviour of human polymorphonuclear neutrophils in direct contact with chitosan-based membranes. *J Biotechnol*. 2007; 132(2):218-226.
24. Ueno H, Murakami M, Okumura M, et al. Chitosan accelerates the production of osteopontin from polymorphonuclear leukocytes. *Biomaterials*. 2001; 22(12):1667-1673.
25. Ueno H, Yamada H, Tanaka I, et al. Accelerating effects of chitosan for healing at early phase of experimental open wound in dogs. *Biomaterials*. 1999; 20(15):1407-1414.

26. Peluso G, Petillo O, Ranieri M, et al. Chitosan-mediated stimulation of macrophage function. *Biomaterials*. 1994; 15(15):1215–1220.
27. Kojima K, Okamoto Y, Kojima K, et al. Effects of chitin and chitosan on collagen synthesis in wound healing. *J Vet Med Sci*. 2004; 66(12):1595–1598.
28. Wiegand C, Winter D, Hippler UC. Molecular-weight-dependent toxic effects of chitosans on the human keratinocyte cell line HaCaT. *Skin Pharmacol Physiol*. 2010; 23(3):164–170.
29. Howling GI, Dettmar PW, Goddard PA, et al. The effect of chitin and chitosan on the proliferation of human skin fibroblasts and keratinocytes in vitro. *Biomaterials*. 2001; 22(22):2959–2966.
30. Nascimento EG, Sampaio TB, Medeiros AC, et al. Evaluation of chitosan gel with 1% silversulfadiazine as an alternative for burn wound treatment in rats. *Acta Cir Bras*. 2009; 24(6):460–465.
31. Klokkevold PR, Vandemark L, Kenney EB, et al. Osteogenesis enhanced by chitosan (poly-N-acetyl glucosaminoglycan) in vitro. *J Periodontol*. 1996; 67(11):1170–1175.
32. Degim Z, Celebi N, Sayan H, et al. An investigation on skin wound healing in mice with a taurine-chitosan gel formulation. *Amino Acids*. 2002; 22(2):187–198.
33. Service RF. Tissue engineers build new bone. *Science*. 2000; 289: 1498–500.
34. Di Martino, A.; Sittering, M.; Risbud, M.V. Chitosan: A versatile biopolymer for orthopaedic tissue-engineering. *Biomaterials*. 2005; 26:5983–5990.
35. Hu, Q.; Li, B.; Wang, M.; Shen, J. Preparation and characterization of biodegradable chitosan/hydroxyapatite nanocomposite rods via in situ hybridization: a potential material as internal fixation of bone fracture. *Biomaterials*. 2004; 25: 779–785.
36. Teng, S.; Lee, E.; Yoon, B.; Shin, D.; Kim, H.; Oh, J. Chitosan/nanohydroxyapatite composite membranes via dynamic filtration for guided bone regeneration. *J. Biomed. Mater. Res. Part A*. 2009; 88: 569–580.
37. Chen, F.; Wang, Z.; Lin, C. Preparation and characterization of nano sized hydroxyapatite particles and hydroxyapatite/chitosan nano-composite for use in biomedical materials. *Mater.Lett*. 2002, 57, 858–861.
38. Zhang, Y.; Venugopal, J.R.; El-Turki, A.; Rama krishna, S.; Su, B.; Lim, C.T. Electrospun biomimetic nanocomposite nanofibers of hydroxyapatite/chitosan for bone tissue engineering. *Biomaterials* 2008, 29, 4314–4322.
39. Xianmiao, C.; Yubao, L.; Yi, Z.; Li, Z.; Jidong, L.; Huanan, W. Properties and in vitro biological evaluation of nano-hydroxyapatite/chitosan membranes for bone guided regeneration. *Mater. Sci. Eng. C*. 2009; 29: 29–35.
40. Kong, L.; Gao, Y.; Cao, W.; Gong, Y.; Zhao, N.; Zhang, X. Preparation and characterization of nano-hydroxyapatite/chitosan composite scaffolds. *J. Biomed. Mater. Res. Part A*. 2005; 75A: 275–282.
41. Manjubala, I.; Ponomarev, I.; Wilke, I.; Jandt, K. Growth of osteoblast like cells on biomimetic apatite-coated chitosan scaffolds. *J. Biomed. Mater. Res. Part A: Appl. Biomater*. 2008; 8: 7–16.
42. Thein-Han, W.; Misra, R. Biomimetic chitosan–nanohydroxyapatite composite scaffolds for bone tissue engineering. *Acta Biomater*. 2009; 5: 1182–1197.
43. Oliveira, J.; Rodrigues, M.; Silva, S.; Malafaya, P.; Gomes, M.; Viegas, C.; Dias, I.; Azevedo, J.; Mano, J.; Reis, R. Novel hydroxyapatite/chitosan bilayered scaffold for osteochondral tissue-engineering applications: Scaffold design and its performance when seeded with goat bone marrow stromal cells. *Biomaterials*. 2006; 27: 6123–6137.
44. Ding, S. Biodegradation behavior of chitosan/calcium phosphate composites. *J. Non-Cryst. Solids*. 2007; 353: 2367–2373.
45. Yamaguchi, I.; Tokuchi, K.; Fukuzaki, H.; Koyama, Y.; Takakuda, K.; Monma, H.; Tanaka, J. Preparation and microstructure analysis of chitosan/hydroxyapatite nanocomposites. *J. Biomed. Mater. Res*. 2001; 55: 20–27.
46. Kim, S.-K.; Mendis, E. Bioactive compounds from marine processing byproducts-A review. *Food Res. Int*. 2006; 39: 383–393.
47. Nath, S.; Dey, A.; Mukhopadhyay, A.K.; Basu, B. Nanoindentation response of novel hydroxyapatite-mullite composites. *Mater. Sci. Eng. A*. 2009; 513–514: 197–201.